

Technical Data Sheet **PEI 1110-WHT**

ProPolymers PEI 1110-WHT is a white pigmented polyetherimide that offers a superior combination of mechanical, electrical, and thermal properties. PEI is inherently flame resistant with low smoke emission. It provides outstanding processability and good chemical resistance.

Mechanical	ASTM	English	Metric
Tensile Strength at Yield	D 638	16,000 psi.	105 Mpa
Elongation at Fail	D 638	60.0%	60.0%
Elongation at Yield	D 638	10.0%	10.0%
Flexural Modulus	D 790	540,000 psi.	3,300 Mpa
Flexural Strength	D 790	24,000 psi.	160 Mpa
Izod Impact Strength, Notched	D 256	1.0 ft-lb/in	6 kJ/m ²
Izod Impact Strength, Unnotched	D 256	25.0 ft-lb/in	140 kJ/m ²
Thermal			
Vicat Softening Temp	D1525	426 F	219 C
Deflection Temperature@ 66psi	D 648	410 F	210 C
Deflection Temperature @ 264psi	D 648	390 F	199 C
Coefficient of Thermal Expansion	D 696	3.0X10 ⁻³ %/F	5.0X10 ⁻³ %/C
Misc.			
Specific Gravity	D 792	1.35	1.35
Water Absorption (24hr.)	D 570	0.25%	0.25%
Hardness, Rockwell M		109	109
Melt Flow Rate, 337C/6.6 kgf	D 1238	15.0 g/10 min.	15.0 g/10 min.
Mold Shrinkage, flow, 125-180 mil	D 955	5-8 in/in E-3	5-8 cm/cm E-3
Mold Shrinkage, xflow, 125-180 mil	D 955	6-9 in/in E-3	6-9 cm/cm E-3

The data listed above are typical properties, and as such are dependent on processing conditions. No warranties, expressed or implied, including patent warranties, or warranties of merchantability or fitness for use, are made with respect to the product information.

